

ORIGINAL

Open Access

Removal of ethidium bromide by carbon nanotube in aqueous solution: isotherms, equilibrium mechanism studies, and its comparison with nanoscale of zero valent iron as adsorbent

Fahimeh Najafi^{1*}, Mehdi Norouzi², Karim Zare^{3,4} and Ali Fakhri⁵

Abstract

The adsorption of ethidium bromide (EtBr) by single-walled carbon nanotubes (SWCNTs) and nanoscale of zero valent iron (NZVI) were investigated to assess its possible use as adsorbents. The effect of various factors, namely initial adsorbate concentration, adsorbent dosage, and contact time, were studied to identify adsorption capacity of SWCNTs and NZVI surfaces. The experiment demonstrated the maximum EtBr which was obtained at 5 min to attain equilibrium for SWCNTs and NZVI surfaces. Adsorption data were modeled with the Langmuir, Freundlich, and Temkin isotherms. Langmuir adsorption model was used for the mathematical description of the adsorption equilibrium, and the equilibrium data fitted very well with this model for both surfaces as adsorbents. The study showed that SWCNTs and NZVI surfaces could be used as new and efficient adsorbent materials for the removal of EtBr from aqueous solution. Also, the result showed that the SWCNTs were more effective than NZVI in the removal of EtBr from aqueous solution.

Keywords: Ethidium bromide; Single-walled carbon nanotube; NZVI; Removal; Isotherms; Kinetics

Background

Ethidium bromide (EtBr; 3,8-diamino-6-phenyl-5-ethyl-phenanthridinium bromide), commonly used in research laboratories as a stain for the visualization of nucleic acids in electrophoresis gels, is a toxic chemical and a potent mutagen [1]. When used in nucleic acid staining, ethidium bromide fluoresces a red-orange to pink color under ultraviolet light and with increased fluorescence when bound to double-stranded DNA. While it is not specifically regulated as a hazardous waste, the mutagenic properties may present health hazards and disposal concerns if it is not managed properly in the laboratory [2]. Adsorption has been found to be an effective and economical method with high potential for the removal, recovery, and recycle of pollution from the wastewater [3]. In this decade, the use of single-walled carbon nanotubes (SWCNTs) and nanoscale of zero valent iron

(NZVI) as a reactive medium for the treatment of toxic chemicals is one of the most significant techniques and has attracted a lot of attention because the iron metal is of low cost, low toxicity, is easy to get, and has good effectiveness and ability to degrading contaminants. Laboratory studies have demonstrated that SWCNTs and NZVI surfaces as adsorbents can effectively transform chlorinated solvents, organochlorine pesticides, organic dyes and heavy metals [4-11] into nontoxic forms. Nanoscale of zero valent iron has drawn great attention as an inexpensive and environmentally friendly strong reducing agent [12,13]. Addition of NZVI to oxygen-containing water results in oxidation of organic compounds [14]. Therefore, extensive efforts have been directed to assess the potential application of NZVI for the decomposition of organic pollutants in the wastewater. SWCNTs, ever since their discovery, have attracted extensive attention due to their unique properties. They have shown potential applications in many areas, such as conductive and high-strength composites. With the significant increase in production and use of SWCNTs, one major concern is the

* Correspondence: fahimnajafi@gmail.com

¹Department of Chemistry, Roudehen Branch, Islamic Azad University, Roudehen, Iran

Full list of author information is available at the end of the article




Figure 1 SEM images of SWCNT and NZVI surfaces before and after reaction. Before reaction (a,c, respectively) and after reaction (b,d, respectively) with EtBr molecules in aqueous solution.

health and environmental risks posed by these nano-materials once they are released to the environment. Evidences for potential risks of SWCNTs to humans and ecosystems are accumulating rapidly [15]. Due to their highly hydrophobic surfaces, SWCNTs exhibit strong adsorption affinities to synthetic organic chemicals, such as polycyclic aromatic hydrocarbons. As a consequence, toxicity of SWCNTs may be further enhanced by adsorption of toxic chemicals. Therefore, understanding of SWCNT interactions is critical for the environmental of both SWCNTs and toxic pollutants as well as for the applications of SWCNTs as potential adsorbents [16].

The objective of this research is to investigate the adsorption kinetics and isotherm models of EtBr removal by SWCNT and NZVI surfaces. Equilibrium data can be used to predict the rate at which the target contaminant is removed from aqueous solutions, and equilibrium adsorption isotherms are used to quantify the adsorptive capacity of an adsorbent. Results from this study can be used to assess the utility of SWCNT and NZVI surfaces for EtBr removal, in particular EtBr adsorption, at the field scale.

Results and discussion

Characterization of the adsorbent

Figure 1 shows the SEM image of freshly synthesized SWCNTs (a,b) and iron nanoparticles (c,d). It can be observed that the iron particles are in the form of nanospheres, which exist in contact with each other and form chains having diameters of 50 to 100 nm [17].




Figure 2 The effect of contact time on removal of EtBr by (a) SWCNT and (b) NZVI surfaces. (a) Initial concentration, 20 mg/L; adsorbent dosage, 30 mg; and temperature = 20°C ± 0.1°C. (b) Initial concentration, 20 mg/L; adsorbent dosage, 30mg; and temperature = 20°C ± 0.1°C.




Figure 1b,d showed that the EtBr molecules removed by SWCNT and NZVI surfaces were covered in aqueous solution.

Effect of contact time

In these experiments, initial concentration of EtBr molecules on SWCNT and NZVI surfaces was 20 mg/L (Figure 2). The effects of contact time (0 to 10 min) were investigated at 20 mg/50 mL sample dosage. The extent of removal of EtBr by SWCNT and NZVI surfaces was found to increase and has reached its maximum with the increase in contact time. The time at which the maximum percentage removal of EtBr occurs is fixed as the contact time (Figure 2a for the removal of SWCNTs and Figure 2b for the removal of NZVI).

Effect of initial EtBr concentration

The effect of initial concentration (10 to 40 mg/L) of EtBr adsorption on to SWCNTs and NZVI surfaces are presented in Figure 3 (Figure 3a for the removal of SWCNTs and Figure 3b for the removal of NZVI). A rapid removal is observed at the initial stages, and it then proceeds slowly until equilibrium is reached. This may be due to the availability of the number of vacant adsorption sites at the initial stage. The equilibrium


adsorption capacity of SWCNT and NZVI surfaces were decreased as there is increasing concentration from 10 to 40 mg/L. At lower EtBr concentration, the available adsorption sites are relatively high, and consequently, the EtBr species can easily find the accessible adsorption sites for both adsorbents (SWCNT and NZVI surfaces).

Effect of adsorbent dosage

From Figure 4 (Figure 4a for the removal of SWCNTs and Figure 4b for the removal of NZVI), we see that the optimum dose of SWCNT and NZVI surfaces for the EtBr were 30 mg/50 mL. Though at 40 mg/50 mL, there is a slight increase in adsorption value, but if we get nearly the same result as we get at an adsorbent dosage of 50 mg/50 mL, then going for 70 mg/50 mL will be expensive and there will be loss of adsorbent. It is obvious, with increasing the amount, what the active sites are for adsorption of three dyes.

Effect of temperature

To study the effect of temperature on the removal of EtBr, the experiments were carried out at temperatures varying from 283 to 313 K. It is revealed from Figure 5 (Figure 5a for the removal of SWCNTs and Figure 5b






Figure 5 Effect of temperature on the removal of EtBr by (a) SWCNT and (b) NZVI surfaces. (a) Initial concentration, 20 mg/L; contact time, 5 min; and adsorbent dosage, 30 mg. (b) Initial concentration, 20 mg/L; contact time, 5 min; and adsorbent dosage, 30 mg.

for the removal of NZVI), that the removal of EtBr with temperatures would increase the mobility of the EtBr and produce a swelling effect within the internal structure of adsorbent thus enabling the large molecules of EtBr to penetrate further. The greater removal of EtBr due to increasing temperature may have more interaction between the adsorbate and adsorbent.

Adsorption isotherms

Equilibrium isotherm equations are used to describe the experimental adsorption data. In this study, three adsorption models, that is the Langmuir, Freundlich, and Temkin isotherms, were used to describe the reactive dye equilibrium. The Langmuir isotherm [18] which is valid for monolayer sorption onto a completely homogeneous surface with a finite number of identical sites and with negligible interaction between adsorbed molecules is given by Equation 1:

$$q_e = \frac{q_m K_L C_e}{(1 + K_L C_e)}, \quad (1)$$

where q_e (mg/g) and C_e (mg/L) are the amount of adsorbed EtBr per unit mass of adsorbent and an adsorbed EtBr concentration in solution at equilibrium, respectively. q_m is the maximum amount of the EtBr per unit mass of adsorbent to form a complete monolayer on the surface




Figure 6 Langmuir plots. (a) Langmuir plots (Type 1A; Type 2B) for EtBr removal by SWCNTs. (b) Langmuir plots (Type 1A; Type 2B) for EtBr removal by NZVI.

bound at high C_e (mg/g), and K_L is a constant related to the affinity of the binding sites (L/mg). The two linear transformations of the Langmuir isotherm is often expressed as Equation 2 (Type1) and Equation 3 (Type 2):

$$\frac{C_e}{q_e} = \frac{1}{K_L q_m} + \frac{C_e}{q_m}, \quad (2)$$

$$\frac{1}{q_e} = \frac{1}{q_m} + \frac{1}{K_L q_m C_e}, \quad (3)$$

The essential characteristics of the Langmuir equation can be expressed in terms of a dimensionless separation factor, R_L , defined by [19]:

$$R_L = \frac{1}{1 + K C_0}, \quad (4)$$

where C_0 is the initial EtBr concentration (mg/L). R_L values indicate the type of isotherm to be irreversible ($R_L = 0$), favorable ($0 < R_L < 1$), linear ($R_L = 1$), or unfavorable ($R_L > 1$). The empirical Freundlich isotherm based on sorption on a heterogeneous surface is given by Equation 5 [20]:

$$q_e = K_F C_e^{1/n}, \quad (5)$$

or can be written in linearized form (Equation 6) as:

$$\ln q_e = \ln K_F + \frac{1}{n} \ln C_e, \quad (6)$$

where K_F and n are the Freundlich constants characteristic of the system. K_F and n are indicators of adsorption capacity and adsorption intensity, respectively. q_e is the equilibrium EtBr concentration in solid phase (mg/g), and C_e is the equilibrium EtBr concentration in liquid phase (mg/L). Temkin isotherm contains a factor that explicitly takes into the account the adsorbing species-adsorbent interactions. The Temkin equation is given as [21]:

$$q_e = \frac{RT}{b} \ln K_T C_e, \quad (7)$$

which can be linearized as:

$$q_e = B_T \ln K_T + B_T \ln C_e, \quad (8)$$

where $B_T = RT/b$, T (K) is the absolute temperature, R (8.314 J/mol) is the universal gas constant, K_T (per milligram) is the equilibrium binding constant, and b (J/mol) is related to the heat of adsorption. The isotherm constants K_T and B_T are calculated from the slope and intercept of the q_e versus $\ln C_e$ plot. The plots of linearized Langmuir, Freundlich, and Temkin isotherms are illustrated in Figures 6, 7, and 8, respectively. Parameters of the three isotherms were calculated and listed in Table 1. Based on the values of R^2 , it can be concluded that the Langmuir isotherm best fits the equilibrium data. The




Figure 7 Freundlich plots. (a) Freundlich plots for EtBr adsorption by SWCNTs. (b) Freundlich plots for EtBr adsorption by NZVI.




Figure 8 Temkin plots. (a) Temkin plots for EtBr adsorption by SWCNTs. (b) Temkin plots for EtBr adsorption by NZVI.

Table 1 Isotherm parameters for the adsorption of EtBr by SWCNTs

Langmuir (Type 1)			Langmuir (Type 2)				Freundlich				Temkin		
K_L (L/g)	q_m (mg/g)	R^2	R_L	K_L (L/g)	q_m (mg/g)	R^2	R_L	K_F (mg/g)/(mg/L) ^{1/n}	n	R^2	K_T (m/g)	b (J/mol)	R^2
0.2001	45.111	0.9994	0.5	0.1186	42.160	0.9994	0.6	5.4286	1.733	0.9955	1.1370	270.01	0.9990

maximum adsorption capacity (q_m) of adsorbent calculated from Langmuir isotherm defines the total capacity of the adsorbent for EtBr. The values of R_L calculated from Equation 4 are listed in Table 2. The R_L values are between 0 and 1, and the adsorption process is favorable. The fact that the Langmuir isotherm fits the experimental data very well may be due to the homogeneous distribution of active sites on the SWCNTs and NZVI surface because application of the Langmuir equation involves the assumption that the surface were homogeneous.

Conclusions

The removal of ethidium bromide by SWCNTs and nanoparticle zero valent iron were studied in a batch system with respect to the temperature, adsorbent dose, and contact time. Removal of EtBr from aqueous solution was possible using SWCNTs and NZVI surfaces. It was seen that maximum adsorption takes place after 5 to 7 min. The optimum doses of adsorbents were 30 mg for NZVI. The Langmuir, Freundlich, and Temkin isotherm models provided the best fits to predict the adsorption for the EtBr by SWCNTs and NZVI surfaces. From the above results, we conclude that the adsorbent NZVI was effective in removing EtBr from aqueous solution. Also, the removal of EtBr by SWCNT surfaces was more effective than that of NZVI surfaces.

Methods


Materials

Ethidium bromide was supplied by Merck, Darmstadt, Germany (maximum purity available). All solutions were prepared with deviations of less than $\pm 0.1\%$ from the desired concentrations. SWCNTs (Armchair (6,6), purity >95; diameter, 1 to 2 nm; length, 5 to 30 nm; surface area, 400 m²/g; and manufacturing method, catalytic chemical vapor deposition).

Preparation of NZVI particles

NZVI particles were prepared by liquid-phase reduction method. All solvents were degassed and saturated

for 30 min with N₂ before use. NZVI was synthesized by adding 1 M NaBH₄ solution into 0.5 M FeCl₃ solution during vigorous stirring under N₂ atmosphere. The mixture's color turned from red brown to light yellow and then eventually to black. At the same time, the mixture gradually produced more black grain particles in the three-neck flask. Ferric iron (Fe⁺³) was reduced to elemental iron according to the following reaction:



Then, black NZVI particles were vacuum-filtered and washed with deionized water and 1:1 (V/V) ethanol/acetone; doing so prevented the NZVI from oxidizing, and then, resulting gray-black solid was dried under nitrogen atmosphere before use.

Batch equilibrium studies

Adsorption experiments were carried out by agitating 50 mg of SWCNTs and NZVI for each individually in aqueous solution with 30 ml of EtBr solution of desired concentration for each surfaces (SWCNTs and NZVI) and pH at 180 rpm, 25°C in a thermostated mechanical shaker (ORBITEK, Chennai). Concentration of EtBr was estimated spectrophotometrically by monitoring the absorbance at 274 nm using a UV-vis spectrophotometer (Hitachi model 8543, Chiyoda-ku, Japan).

The effect of adsorbent dosage was studied by agitating 30 mL of EtBr solutions with different adsorbent doses (10 to 70 mg) at equilibrium time. The amounts of EtBr adsorbed by the adsorbent were calculated using the following equation:

$$\frac{(C_0 - C_t)V}{W}, \quad (9)$$

where C_0 is the initial EtBr concentration, C_t is the EtBr concentration (mg/L) at any time, V is the volume of solution (L), and W is the mass of the adsorbents (g).

Table 2 Isotherm parameters for the adsorption of EtBr by NZVI

Langmuir (Type 1)			Langmuir (Type 2)			Freundlich				Temkin			
K_L (L/g)	q_m (mg/g)	R^2	R_L	K_L (L/g)	q_m (mg/g)	R^2	R_L	K_F (mg/g)/(mg/L) ^{1/n}	n	R^2	K_T (m/g)	b (J/mol)	R^2
0.1106	43.290	0.9981	0.4	0.1186	42.160	0.9991	0.5	5.3275	1.626	0.9940	1.1261	264.94	0.9911

Competing interests

The authors declare that they have no competing interests.

Authors' contributions

FN carried out the result analysis, participated to draft the manuscript and in the manuscript elaboration, carried out the experiments, and obtained most of the experimental images. MN, KZ, and AF coordinated the project, discussed the results, and helped to draft the manuscript. All authors read and approved the final manuscript.

Acknowledgements

The authors would like to thank the Islamic Azad University Roudehen Branch for their financial support.

Author details

¹Department of Chemistry, Roudehen Branch, Islamic Azad University, Roudehen, Iran. ²Department of Virology, School of Public Health and Institute of Health Research, Tehran University of Medical Sciences, Tehran, Iran. ³Department of Chemistry, Science and Research Branch, Islamic Azad University, Tehran, Iran. ⁴Department of Chemistry, Shahid Beheshti University, Evin, Tehran, Iran. ⁵Department of Chemistry, Shahre-Qods Branch, Islamic Azad University, Tehran, Iran.

Received: 27 May 2013 Accepted: 28 May 2013

Published: 29 July 2013

References

- Lunn, G, Sansone, EB: Ethidium bromide: destruction and decontamination of solutions. *Anal Biochem* **162**, 453–458 (1987)
- Bountiff, L, Levantis, P, Oxford, J: Electrophoretic Analysis of Nucleic Acids Isolated from Scrapie-infected Hamster Brain. *J Gen Virol* **77**, 2371–2378 (1996)
- Bailey, SE, Olin, TJ, Bricka, RM, Adrian, DD: A review of potentially low-cost sorbents for heavy metals. *Water Res* **33**, 2469–2479 (1999)
- Uzum, C, Shahwan, T, Eroglu, AE, Lieberwirth, I, Scott, TB, Hallam, KR: Application of zero-valent iron nanoparticles for the removal of aqueous Co^{2+} ions under various experimental conditions. *Chem Eng J* **144**, 213–220 (2008)
- Cantrell, KJ, Kaplan, DI, Wietsma, TW: Zero-valent iron for the in situ remediation of selected metals in groundwater. *J Hazard Mater* **42**, 201–212 (1995)
- Cho, HH, Park, JW: Sorption and reduction of tetrachloroethylene with zero valent iron and amphiphilic molecules. *Chemosphere* **64**, 1047–1052 (2006)
- Dombek, T, Dolan, E, Schultz, J, Klarup, D: Rapid reductive dechlorination of atrazine by zero-valent iron under acidic conditions. *Environ Pollut* **111**, 21–27 (2001)
- Ghauch, A, Rima, J, Amine, C, Martin-Bouyer, M: Rapid treatment of water contaminated with atrazine and parathion with zero-valent iron. *Chemosphere* **39**, 1309–1315 (1999)
- Noubactep, C: Characterizing the discoloration of methylene blue in $\text{Fe}^0/\text{H}_2\text{O}$ systems. *J Hazard Mater* **166**, 79–87 (2009)
- Noubactep, C, Kurth, AMF, Sauter, M: Evaluation of the effects of shaking intensity on the process of methylene blue discoloration by metallic iron. *J Hazard Mater* **169**, 1005–1011 (2009)
- Noubactep, C: Characterizing the reactivity of metallic iron upon methylene blue discoloration in $\text{Fe}^0/\text{MnO}_2/\text{H}_2\text{O}$ systems. *J Hazard Mater* **168**, 1613–1616 (2009)
- Li, XQ, Elliott, DW, Zhang, WX: Zero-Valent Iron Nanoparticles for Abatement of Environmental Pollutants: Materials and Engineering Aspects. *Crit. Rev. Solid State Mater. Sci.* **31**, 111–122 (2006)
- Noubactep, C: A Critical review on the process of contaminant removal in $\text{Fe}^0\text{-H}_2\text{O}$ systems. *Environ. Technol.* **29**, 909–920 (2008)
- Noradoun, CE, Cheng, IF: EDTA Degradation Induced by Oxygen Activation in a Zerovalent Iron/Air/Water System. *Environ. Part Sci Technol* **39**, 7158–7163 (2005)
- Wang, H, Zhou, A, Peng, F, Yu, H, Yang, J: Mechanism study on adsorption of acidified multi-walled carbon nanotubes to $\text{Pb}(\text{II})$. *J Colloid Interface Sci* **316**, 277–283 (2007)
- Lu, C, Chiu, H, Liu, C: Removal of zinc(II) from aqueous solution by purified carbon nanotubes: Kinetics and equilibrium studies. *Ind Eng Chem Res* **45**, 2850–2855 (2006)
- Feng, J, Lim, TT: Iron-mediated reduction rates and pathways of halogenated methanes with nanoscale Pd/Fe : Analysis of linear free energy relationship. *Chemosphere* **66**, 1765–1774 (2007)

- Langmuir, I: The adsorption of gases on plane surfaces of glass, mica and platinum. *J Am Chem Soc* **40**, 1361–1368 (1918)
- Mahmoodi, NM, Arami, M: Modeling and sensitivity analysis of dyes adsorption onto natural adsorbent from colored textile wastewater. *J Appl Polym Sci* **109**, 4043–4048 (2008)
- Freundlich, HMF: Über die adsorption in Lösungen (adsorption in solution). *J Phys Chem* **57**, 385–470 (1906)
- Moradi, O, Zare, K, Monajjemi, M, Yari, M, Aghaie, H: The studies of equilibrium and thermodynamic adsorption of $\text{Pb}(\text{II})$, $\text{Cd}(\text{II})$ and $\text{Cu}(\text{II})$ ions from aqueous solution on SWCNTs and SWCNT-COOH surfaces. *Fullerenes, Nanotubes, and Carbon Nanostructures* **18**, 285–302 (2010)

doi:10.1186/2193-8865-3-60

Cite this article as: Najafi et al.: Removal of ethidium bromide by carbon nanotube in aqueous solution: isotherms, equilibrium mechanism studies, and its comparison with nanoscale of zero valent iron as adsorbent. *Journal Of Nanostructure in Chemistry* 2013 **3**:60.

Submit your manuscript to a SpringerOpen[®] journal and benefit from:

- Convenient online submission
- Rigorous peer review
- Immediate publication on acceptance
- Open access: articles freely available online
- High visibility within the field
- Retaining the copyright to your article

Submit your next manuscript at ► springeropen.com